



**HAL**  
open science

**First Eurasian conference on nanotechnology, Baku,  
Azerbaijan photoelectrochemically-assisted bioanode  
constructed by Ru-complex and g-C<sub>3</sub>N<sub>4</sub> coated  
MWCNT electrode**

Bekir Çakiroğlu, Jérôme Chauvin, Karine Gorgy, Mahmut Özacar, Michael Holzinger

► **To cite this version:**

Bekir Çakiroğlu, Jérôme Chauvin, Karine Gorgy, Mahmut Özacar, Michael Holzinger. First Eurasian conference on nanotechnology, Baku, Azerbaijan photoelectrochemically-assisted bioanode constructed by Ru-complex and g-C<sub>3</sub>N<sub>4</sub> coated MWCNT electrode. *Materials Today: Proceedings*, 2020, 10.1016/j.matpr.2019.12.153 . hal-02944836

**HAL Id: hal-02944836**

**<https://cnrs.hal.science/hal-02944836v1>**

Submitted on 24 Apr 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License



ELSEVIER

Available online at [www.sciencedirect.com](http://www.sciencedirect.com)

ScienceDirect

materialstoday:  
PROCEEDINGS

First Eurasian Conference on Nanotechnology, Baku, Azerbaijan  
**Photoelectrochemically-Assisted Bioanode Constructed by Ru-  
Complex and g-C<sub>3</sub>N<sub>4</sub> Coated MWCNT Electrode**

Bekir Çakıroğlu<sup>a,b\*</sup>, Jérôme Chauvin<sup>a</sup>, Karine Gorgy<sup>a</sup>, Mahmut Özacar<sup>b,c</sup>, Michael Holzinger<sup>a,d</sup>

<sup>a</sup>Université Grenoble Alpes, DCM UMR 5250, F-38000, Grenoble, France

<sup>b</sup>Sakarya University, Biomedical, Magnetic and Semiconductor Materials Application and Research Center (BIMAS-RC), 54187, Sakarya, Turkey

<sup>c</sup>Sakarya University, Science & Arts Faculty, Department of Chemistry, 54187, Sakarya, Turkey

<sup>d</sup>CNRS, DCM UMR 5250, F-38000, Grenoble, France

---

## Abstract

In this study, a novel photobioanode was constructed using a Ruthenium complex (Ru-complex) sensitized graphitic carbon nitride (g-C<sub>3</sub>N<sub>4</sub>) nanomaterial deposited on multi-walled carbon nanotubes (MWCNT). g-C<sub>3</sub>N<sub>4</sub> coated MWCNT bearing Ru-complex acts as a platform for the immobilization of flavin adenine dinucleotide dependent glucose dehydrogenase (FADGDH). The formed photosensitive bioanode showed an enhancement in glucose oxidation current under visible light irradiation. The electrocatalytic current increase for in glucose oxidation are possibly due to the good electrical contacting of the immobilized FADGDH on the electrode surface and utilization of light energy. The spectroscopic properties of g-C<sub>3</sub>N<sub>4</sub> and Ru-complex in dimethylformamide (DMF) were determined by UV-visible absorption spectra demonstrating the characteristic absorption peaks in the visible light region. Upon visible light illumination, the enzymatic photoanode revealed a prompt rise in photocurrent (ca. 1.44 μA cm<sup>-2</sup>) compared to the photoelectrode without enzyme (0.65 μA cm<sup>-2</sup>). Light irradiation of the bioanode improved the overall performance of the electrode as glucose oxidation was reinforced by photoelectrochemical (PEC) process.

**Keywords:** MWCNT; FADGDH; g-C<sub>3</sub>N<sub>4</sub>; Ru-complex; Photoelectrochemical bioanode; Glucose oxidation

## Introduction

Solar energy is the most abundant renewable energy resource on earth. To take more advantage of such huge amount of energy, tremendous researches on harnessing of solar energy have been carried out. The biofuel cells (BFC) can convert chemical energy directly into electricity [1]. Combining sunlight harnessing materials with BFCs enables us to achieve dual-directional energy conversion *viz.* light and chemical energy to electricity and can lead to further improvement in BFC performances [2]. Nowadays, the direct generation of electrical energy from sunlight and a biofuel by using a photoelectrochemical biofuel cell (PEBFC) is a hot topic [3]. PEBFCs have been constructed with an efficient photon-to-electron approach to boost the energy conversion efficiency. Accordingly, photoanodes and photocathodes have been constructed for the assembly of PEBFC [4].

In this study, a photoelectrochemical bioanode was fabricated by using an electrode composed of Ru-complex and g-C<sub>3</sub>N<sub>4</sub> deposited MWCNT nanomaterial, and the electrochemical response was enhanced under visible light irradiation.

## Materials and Method

For the synthesis of cis-(Bpy-Py<sub>2</sub>)<sub>2</sub>RuCl<sub>2</sub>·2H<sub>2</sub>O (Ru-complex) [5] [6], RuCl<sub>3</sub>·hydrate (6.18 g, 29.8 mmol), 4,4'-bis(4-pyrenyl-1-ylbutyloxy)-2,2'-bipyridine (42.3 g, 60.0 mmol), and LiCl (8.4 g, 2 mmol) were refluxed in reagent grade DMF (5 mL) for 8 h. After cooling down to room temperature, 250 mL of reagent grade acetone was added and the resultant solution was kept at 0 °C overnight. The suspension was then filtrated, washed successively with deionized water (DW) and diethyl ether, and then dried in vacuum (yield: 62%). UV/Vis (DMF) :  $\lambda_{\text{max}} / \text{nm}$  ( $\epsilon / \text{M}^{-1} \text{cm}^{-1}$ ) = 385 (2880), 440 (1280), 490 (960). g-C<sub>3</sub>N<sub>4</sub> was obtained from our previous study [7]. The MWCNT coated glassy carbon electrodes (GCE) were obtained by drop-casting 25  $\mu\text{L}$  of a sonicated MWCNT dispersion in (N-Methyl-2-pyrrolidone) NMP (5mg mL<sup>-1</sup>) and dried in vacuum. Then 5  $\mu\text{L}$  of g-C<sub>3</sub>N<sub>4</sub> in NMP (1 mg mL<sup>-1</sup>) was coated and dried in vacuum. 10  $\mu\text{L}$  of Ru-complex solutions in DMF (0.6 mM) were applied on the electrode and dried in vacuum. After complex deposition, the electrodes were rinsed several times with DW to remove unbound complexes. FADGDH was immobilized by dropping 20  $\mu\text{L}$  enzyme solution in phosphate buffered saline (PBS) pH 7 (5 mg mL<sup>-1</sup>) on the electrode surface and left at 4 °C overnight. The modified GCE was rinsed with PBS to remove the loosely bound FADGDH. Finally, Nafion in methanol (0.5%) was applied on the electrodes and the resulting PEC bioanodes (designated as GCE/MWCNT-g-C<sub>3</sub>N<sub>4</sub>-Ru (Bpy-Py<sub>2</sub>)<sub>2</sub> Cl<sub>2</sub>-FADGDH) were stored at 4 °C.

## Results and discussion

### *Characterization of Ru-complex*

Schematic illustration of assembly of the PEC bioanode was given in Figure 1. Only a single-monolayer of Ru-complex in a good contact with g-C<sub>3</sub>N<sub>4</sub> meet the need for photo-induced electron transfer, and the high surface area of porous MWCNT structure can provide an enhanced sunlight harvesting. Also, MWCNT plays a pivotal role as an efficient electron

acceptor for the light sensitive entity and improve the photocurrent generation [8][9].

It is clear that the absorption of ruthenium complex ranges from 350 nm to 550 nm, mainly in visible light regions (Figure 2). The complex exhibits the first transition at 385 nm (3.22 eV) with a sharp band edge absorption and the second transition at 440 nm (2.82 eV) and third transition at 490 nm (2.53 eV) in the visible range, which can be attributed to the metal to ligand charge transfer band[10]. Ru-complex also reveals band edge emissions at 460 nm (2.70 eV) and 490 nm (2.53 eV), which can be attributed to excimer of pyrene[10].

According to the decay curve of transient absorption, the charge-separated state occurs within 3.66 ns, which indicates that the electron injection into g-C<sub>3</sub>N<sub>4</sub> occurs on a sub-microsecond timescale (Figure 3).

The one electron redox system of the complex is observed at  $E_{1/2} = 0.065$  V vs Ag/AgCl (scan rate, 2 mV s<sup>-1</sup>) in argon saturated 0.1 M PBS pH 7.0 with a peak-to-peak separation ( $\Delta E_p$ ) of 0.13 V (Figure 4). It can be concluded from the cyclic voltammogram that the synthesized Ru complex has a redox potential in a suitable range for mediated electron transfer with FADGDH when taking into consideration of the redox potential of FAD in glucose oxidizing enzymes at ca. -0.45 V vs Ag/AgCl at pH 7.0 [11]. For the driving force of fast and efficient electron transfer, an appropriate potential difference is needed between the mediator and the FAD unit. The higher this difference is, the electron transfer efficiency will increase but will be detrimental in terms of the final cell voltage of a biofuel cell. The choice of mediator is therefore always a compromise.

#### *Photo-generated charge convey through the bio-anode*

Upon visible light illumination, Ru-complex and g-C<sub>3</sub>N<sub>4</sub> are excited to charge separation, and can generate photocurrent in the presence of an electron donor. Herein, glucose was oxidized by the photoelectrochemically-assisted bioanode and gives two electrons to Ru-complex mediator. The injected electrons to the electrode surface migrate through an external circuit to a counter electrode. FAD serves as the electron acceptor in glucose oxidation catalysed by FADGDH, thereby regenerating FADH<sub>2</sub> after the enzymatic oxidation of glucose. The enzyme catalyzed, and Ru complex mediated electron transfer between glucose and the photoanode are reminiscent of a bioanode operation in an enzymatic BFC [8]. All in all, during the photoelectrochemically-assisted glucose oxidation, chemical energy and light energy are both converted into electricity. Under the light illumination, the photocurrent response of GCE/MWCNT-g-C<sub>3</sub>N<sub>4</sub> photoanode poised at 0 V vs. Ag/AgCl was found to be 0.4  $\mu\text{A cm}^{-2}$  and the photocurrent increased to 0.65  $\mu\text{A cm}^{-2}$  for GCE/MWCNT-g-C<sub>3</sub>N<sub>4</sub>-Ru (pyrene)<sub>2</sub> Cl<sub>2</sub> photoelectrode. The photocurrent reached to 1.44  $\mu\text{A cm}^{-2}$  for GCE/MWCNT-g-C<sub>3</sub>N<sub>4</sub>-Ru (pyrene)<sub>2</sub> Cl<sub>2</sub>-FADGDH bioelectrode in 170 mM glucose (Figure 5) by yielding the most enhanced value.

#### *Photoelectrocatalytic activity of the bioanode*

The high activity of FADGDH and good catalytic activity toward light driven glucose oxidation give way to the development of efficient photosensitive electrode. Figure 6 displays the effect of visible light irradiation on anodic bioelectrocatalysis of glucose. The optimum glucose

concentration was chosen as 170 mM according to the reported study, in which concentration enzymatic reaction velocity and electron transfer turned out to be the limiting factor rather than substrate concentration [1]. Under irradiation, the increment in the glucose oxidation current by 4.9% at 0.2 V vs Ag/AgCl verified that the electron transfer kinetics between Ru complex and electrode was improved.

## Conclusion

In summary, a visible light driven bioanode was constructed. The Ru-complex sensitizer was attached to g-C<sub>3</sub>N<sub>4</sub> by  $\pi$ - $\pi$  interactions. The findings from cyclic voltammetry confirmed that the synthesized Ru complex has a suitable redox potential for mediated electron transfer and the electron transfer kinetics between Ru complex and electrode has improved under irradiation. The PEC bioanode generated improved photocurrent under illumination, which could be attributed to efficient light energy utilization along with good electrical contacting between immobilized enzyme and the electrode surface. The PEC bioanode couples the photogenerated charge separation to the FADGDH-catalyzed glucose oxidation. The energy to drive these processes is provided both by incident photons and by solar energy stored in the chemical bonds of glucose. By choosing a cathode with a large reduction potential, the fabricated bioanode can be used in a biofuel cell to boost the overall performance of BFC. The bioanode displayed fast and stable PEC response towards the visible light illumination, which proves its feasibility for the mass production of a new kind of photo-driven biofuel cell by providing an extending insight beyond the conventional biofuel cell.

## Acknowledgment

The French National Centre for Scientific Research (CNRS) is acknowledged for the research budget and Turkish Council of Higher Education is acknowledged for the research scholarship (YÖK YUDAB).

## References

1. Gross AJ, Chen X, Giroud F, Abreu C, Le Goff A, Holzinger M, Cosnier S (2017) A High Power Buckypaper Biofuel Cell: Exploiting 1,10-Phenanthroline-5,6-dione with FAD-Dependent Dehydrogenase for Catalytically-Powerful Glucose Oxidation. *ACS Catal* 7:4408–4416 . doi: 10.1021/acscatal.7b00738
2. Wang K, Yang J, Feng L, Zhang Y, Liang L, Xing W, Liu C (2012) Photoelectrochemical biofuel cell using porphyrin-sensitized nanocrystalline titanium dioxide mesoporous film as photoanode. *Biosens Bioelectron* 32:177–182 . doi: 10.1016/j.bios.2011.11.056
3. Yu Y, Xu M, Dong S (2016) Photoenergy storage and power amplification strategy in membrane-less photoelectrochemical biofuel cells. *Chem Commun* 52:6716–6719 . doi: 10.1039/c6cc02267g
4. Yu Y, Han Y, Xu M, Zhang L, Dong S (2016) Automatic illumination compensation device based on a photoelectrochemical biofuel cell driven by visible light. *Nanoscale* 8:9004–9008 . doi: 10.1039/c6nr00759g
5. Reuillard B, Le Goff A, Cosnier S (2014) Non-covalent double functionalization of carbon nanotubes with a NADH oxidation Ru(ii)-based molecular catalyst and a NAD-

- dependent glucose dehydrogenase. *Chem Commun* 50:11731–11734 . doi: 10.1039/c4cc04758c
6. Sullivan BP, Salmon DJ, Meyer TJ (1978) Mixed Phosphine 2,2'-Bipyridine Complexes of Ruthenium. *Inorg Chem* 17:3334–3341 . doi: 10.1021/ic50190a006
  7. Çakıroğlu B, Demirci YC, Gökgöz E, Özacar M (2019) A Photoelectrochemical Glucose and Lactose Biosensor Consisting of Gold Nanoparticles, MnO<sub>2</sub> and g-C<sub>3</sub>N<sub>4</sub> decorated TiO<sub>2</sub>. *Sensors Actuators B Chem* 282:282–289 . doi: 10.1016/j.snb.2018.11.064
  8. Gross AJ, Holzinger M, Cosnier S (2018) Buckypaper bioelectrodes: Emerging materials for implantable and wearable biofuel cells. *Energy Environ Sci* 11:1670–1687 . doi: 10.1039/c8ee00330k
  9. Çakıroğlu B, Özacar M (2018) A Self-Powered Photoelectrochemical Glucose Biosensor Based on Supercapacitor Co<sub>3</sub>O<sub>4</sub>-CNT Hybrid on TiO<sub>2</sub>. *Biosens Bioelectron* 119:34–41 . doi: 10.1016/j.bios.2018.07.049
  10. Vonlanthen M, Cevallos-Vallejo A, Aguilar-Ortíz E, Ruiu A, Porcu P, Rivera E (2016) Synthesis, characterization and photophysical studies of novel pyrene labeled ruthenium (II) trisbipyridine complex cored dendrimers. *Polymer (Guildf)* 99:13–20 . doi: 10.1016/j.polymer.2016.06.061
  11. Kavanagh P, Leech D (2013) Mediated electron transfer in glucose oxidising enzyme electrodes for application to biofuel cells: Recent progress and perspectives. *Phys Chem Chem Phys* 15:4859–4869 . doi: 10.1039/c3cp44617d




Figure 1. Assembly of GCE/MWCNT-g-C<sub>3</sub>N<sub>4</sub>-cis-(Bpy-Py<sub>2</sub>)<sub>2</sub>RuCl<sub>2</sub>




Figure 2. Absorbance and fluorescence spectra of Ru-complex (in DMF, excitation wavelength: 430 nm)




Figure 3. Luminescence decay curve after laser excitation at 490 nm recorded for Ru complex in deoxygenated DMF ( $1.25 \cdot 10^{-4}$  M).




Figure 4. Cyclic voltammogram of GCE/MWCNT-g-C<sub>3</sub>N<sub>4</sub>- cis-(pyrene)<sub>2</sub>RuCl<sub>2</sub> in argon saturated 0.1 M PBS (pH 7.0) (scan rate, 2 mV s<sup>-1</sup>)




Figure 5. The photocurrent generation for the photoelectrodes in argon saturated 170 mM glucose in 0.1 M PBS (pH 7.0) at 0 V vs Ag/AgCl




Figure 6. Glucose oxidation for the photoelectrodes in argon saturated 0.1 M PBS (pH 7.0) (scan rate, 2 mV s<sup>-1</sup>)