



HAL
open science

Novel self-assembled supramolecular dyads on graphene

Quentin Fernez, Shiva Moradmand, Michele Mattera, William Djampa-Tapi, Céline Fiorini-Debuisschert, Fabrice Charra, David Kreher, Fabrice Mathevet, Imad Arfaoui, Lydia Sosa Vargas

► To cite this version:

Quentin Fernez, Shiva Moradmand, Michele Mattera, William Djampa-Tapi, Céline Fiorini-Debuisschert, et al.. Novel self-assembled supramolecular dyads on graphene. SPIC 2022 : Quatrième congrès national Sciences et Technologies des systèmes pi-conjugués, Dec 2022, Saint-Malo, France. , 10, pp.13981-13988, 2022. hal-04423756

HAL Id: hal-04423756

<https://cnrs.hal.science/hal-04423756v1>

Submitted on 29 Jan 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

INTRODUCTION




To develop new functional materials, nanoscopic scale architecture control is necessary¹. As a bottom-up synthesis strategy, molecular self-assemblies on surface have been explored, and have demonstrated good control of patterning on various surfaces². From these surfaces; graphene is of interest due to its versatility and potential in future semiconductive devices³. The work presented here describes the functionalization of a graphenoid surface via a supramolecular approach.

Chem. Sci. 2018, 9 (8), 2028–2041.

PROJECT GOALS

We aim to synthesis of **versatile** and **functionalized building-blocks** which **self-organize** on **graphenoid surfaces**. We are mainly interested in :

- **Tuning the surface** self-assembly via the functionalisation of the molecular building blocks
- **Grafting a fluorescent functionality** decoupled from the surface
- **Studying by Scanning Tunnelling Microscopy (STM)** the topology of the molecular 2D-assemblies





Design strategy and syntheses

These 'smart' **building-blocks** were designed with the aim to develop a **homogeneous, functional, integrated self-assembly** on a graphenoid surface. With this molecular design strategy we are able to **fine-tune** the self-assembly, **orientation** and **functionality** via modification of:

Functionality: a **perylene (PDI)**; with steric hindrance to avoid its assembly on the surface. It is a strongly fluorescent component. A donor/acceptor unit could replace it.

Linker: a **pyridyl derivative**; decouples the functionality from the surface. Orientation and distance can be controlled by modifying it.




Pedestal: a **phthalocyanine (Pc)**; functionalized on peripheral positions to enable the supramolecular self-assembly on the surface. A non-functionalized phthalocyanine was also used in host guest systems.



- Synthesis : gram to milligram scale (starting materials → final products)
- Sensitive step: cyanation (yield can vary from 20 to 80 %)
- Solubility issues → for PDI (3 first steps), and all of the ZnPcs


Self-assembling properties

The following STM images are monolayers of several molecular pedestals on Highly Oriented Pyrolytic Graphite (HOPG) surfaces.



Dyad association characterization

We then studied the formation of the ZnPc-PDI complexes in solution. Titration experiments were performed by ¹H NMR absorbance, and fluorescence.



CONCLUSION

Alkylated zinc phthalocyanines were synthesized as well as several **perylene diimides** with **different linkers**.

Self-assembling networks of **zinc phthalocyanine** were observed on Surface by STM. The **lattice parameters** are as expected; proportional to the alkyl chain lengths on the zinc phthalocyanines.

In solution, the association of **PDI with ZnPcs** comes from **π-stacking**. The association of **PDI with ZnPs** comes from **metal-ligand interactions**.

FUTURE WORK

