

# Electron-phonon coupling and transient dynamics of hot carriers: from interpretation of photoemission experiments to transport simulations in devices

M Ghanem, P Dollfus, J Saint, R Sen, N Vast, J Sjakste

### ▶ To cite this version:

M Ghanem, P Dollfus, J Saint, R Sen, N Vast, et al.. Electron-phonon coupling and transient dynamics of hot carriers: from interpretation of photoemission experiments to transport simulations in devices. 2024. hal-04519274

## HAL Id: hal-04519274 https://cnrs.hal.science/hal-04519274

Preprint submitted on 25 Mar 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

### Electron-phonon coupling and transient dynamics of hot carriers: from interpretation of photoemission experiments to transport simulations in devices.

M. Ghanem<sup>1</sup>, P.Dollfus<sup>1</sup>, J. Saint Martin<sup>2</sup>, R. Sen<sup>3</sup>, N. Vast<sup>4</sup>, and J. Sjakste<sup>4</sup>

<sup>1</sup>Université Paris Saclay, Centre des Nanosciences et de Nanotechnologies, 91120, Palaiseau, France

<sup>2</sup>Université Paris Saclay, ENS Paris Saclay, CNRS, SATIE, 91190, Gif-sur-Yvette, France

<sup>3</sup>Institut de Minéralogie, de Physiques des Matériaux et de Cosmochimie (IMPMC), Sorbonne Université, UMR 7590, 4 place Jussieu, 75252 Paris Cedex 05, France

<sup>4</sup>Laboratoire des Solides Irradiés, CEA/DRF/IRAMIS, École Polytechnique, CNRS, Institut Polytechnique de Paris, 91120 Palaiseau, France

#### ABSTRACT

The progress in DFT-based description of the electron-phonon scattering allowed to describe the relaxation dynamics of hot or photoexcited electrons in several materials, in very good agreement with time-resolved spectroscopy experiments. As hot carriers also start to attract attention in the context of emerging concepts for energy conversion, here we present our first results related to the coupling of ab initio data with device-oriented Monte Carlo simulation methods. We show that DFT-based description of the electron-phonon intervalley scattering in GaAs, coupled with the stochastic Monte Carlo method, allows to describe the energy transfer from electrons to phonons in transient regime, in good agreement with previous time-resolved photoemission experiments.

Keywords: electron-phonon coupling, semiconductor, photoexcited electrons, Monte Carlo simulations

#### 1. INTRODUCTION

Methods based on density functional theory (DFT) allow today to describe electron-phonon scattering rates from first principles.<sup>1,2</sup> It was shown that electron transport characteristics of many 3D and 2D semiconductors are well described within the approaches which couple DFT with the Boltzmann Transport Equation (BTE).<sup>3</sup> At the same time, the progress in DFT-based description of the electron-phonon scattering also allowed to describe the relaxation dynamics of hot or photoexcited electrons in several materials, in very good agreement with time-resolved spectroscopy experiments.<sup>4,5</sup> For example, in 4, 6, the two-photon photoemission experiments were able to capture both the initial momentum randomization of the photoexcited electrons due to electron-phonon scattering and the energy transfer from electrons to phonons, for electrons photoexcited into the conduction band of GaAs. Both relaxation mechanisms were well described by the DFT-based calculations.<sup>4,6</sup>

In some cases, however, the theoretical approaches which couple DFT description of materials with the *static* BTE turn out to be insufficient. Instead, one has to describe the evolution in time of photoexcited, nonthermal carrier distributions.<sup>7-12</sup> Indeed, time-resolved spectroscopy techniques, such as time- and angle-resolved photoemission spectroscopy as well as phase-resolved transient absorption spectroscopy, provide the possibility to monitor *transient* material characteristics which are due to photoexcited carrier distributions evolving on femtosecond and attosecond time scales.<sup>6,13-16</sup> In a similar way, future generations of energy converters might involve high energy carriers, therefore requiring reliable theoretical approaches to describe the *transient* transport properties of devices.<sup>17,18</sup> Among the numerical methods available for describing the time evolution of carrier distributions, the particle Monte Carlo method for solving the BTE provides reliable, numerically stable results

jelena.sjakste@polytechnique.edu

at low numerical cost.<sup>19</sup> This approach makes it possible to capture carrier distributions far from equilibrium, and to take into account complex diffusion mechanisms with highly anisotropic behavior.

In this work, we discuss the coupling of device-oriented the stochastic Monte Carlo (MC) approach<sup>20–22</sup> with the *ab initio* description of the electron-phonon coupling,<sup>23,24</sup> in the case of GaAs. It must be noted that some of the specific problems encountered when the effective electron-phonon coupling constants calculated with DFTbased methods are coupled with MC approaches were discussed e.g. in Ref. 25 for silicon, and, recently, in Refs. 26,27 for GaAs. In the present work, we focus specifically on the energy transfer from electrons to phonons in transient regime, which is governed by the intervalley electron-phonon scattering, as was shown e.g. in Ref. 4.

The paper is organized as follows. First, we will present briefly the theoretical framework and technical details of our DFT and MC calculations. Then, we will present the results of the MC simulation of the energy transfer rate from the photoexcited electrons to phonons, coupled to DFT-based intervalley scattering parameters. We will show that DFT-based description of the electron-phonon intervalley scattering in GaAs, coupled with the stochastic Monte Carlo method, allows to describe the energy transfer from electrons to phonons in transient regime, in good agreement with previous time-resolved photoemission experiments.

#### 2. THEORETICAL FRAMEWORK AND COMPUTATIONAL DETAILS

The total electron-phonon scattering rate, or self-energy, is implemented, e.g., in the EPIq  $code^{23}$  and defined in numerous other works:<sup>4, 28–30</sup>

$$\Gamma_{n,\mathbf{k}} = \Gamma_{em} + \Gamma_{abs} \tag{1}$$

where

$$\Gamma_{em} = \frac{2\pi}{\hbar} \Sigma_{m\nu} \int \frac{d\mathbf{q}}{\Omega_{BZ}} |g_{mn\nu}(\mathbf{k}, \mathbf{q})|^2 (N_{\mathbf{q},\nu} + 1 - f_{m,\mathbf{k}+\mathbf{q}}) \delta(\varepsilon_{n,\mathbf{k}} - \varepsilon_{m,\mathbf{k}+\mathbf{q}} - \hbar\omega_{\mathbf{q}\nu})$$

$$\Gamma_{abs} = \frac{2\pi}{\hbar} \Sigma_{m\nu} \int \frac{d\mathbf{q}}{\Omega_{BZ}} |g_{mn\nu}(\mathbf{k}, \mathbf{q})|^2 (N_{\mathbf{q},\nu} + f_{m,\mathbf{k}+\mathbf{q}}) \delta(\varepsilon_{n,\mathbf{k}} - \varepsilon_{m,\mathbf{k}+\mathbf{q}} + \hbar\omega_{\mathbf{q}\nu})$$
(2)

Here, all emission and absorption processes allowed by energy and momentum conservation are taken into account.  $g_{mn\nu}(\mathbf{k}, \mathbf{q})$  stand for the electron-phonon matrix elements between electronic states with m and n band numbers, coupled via the phonon mode  $\nu$ .  $N_{\mathbf{q},\nu}$  stand for phonon population numbers (Bose-Einstein distribution),  $f_{n,\mathbf{k}}$  is the electron Fermi-Dirac distribution function,  $\varepsilon_{n,\mathbf{k}}$  are electron eigenenergies and  $\omega_{\mathbf{q}\nu}$  are phonon frequencies. The total electron-phonon scattering rate expresses the probability for an excited electron to change its initial momentum, i.e. to be scattered elsewhere in the Brillouin zone.<sup>4,6</sup>

The density of final electronic states *FDOS* represents the phase space available for scattering from a given initial electronic state, it is determined by the energy and momentum conservation rules and by the temperature *via* the phonon occupation numbers (i.e. *via* Bose-Einstein coefficients):

$$FDOS_{n,\mathbf{k}} = \frac{2\pi}{\hbar} \Sigma_{m\nu} \int \frac{d\mathbf{q}}{\Omega_{BZ}} \left[ (N_{\mathbf{q},\nu} + 1 - f_{m,\mathbf{k}+\mathbf{q}}) \delta(\varepsilon_{n,\mathbf{k}} - \varepsilon_{m,\mathbf{k}+\mathbf{q}} - \hbar\omega_{\mathbf{q}\nu}) + (N_{\mathbf{q},\nu} + f_{m,\mathbf{k}+\mathbf{q}}) \delta(\varepsilon_{n,\mathbf{k}} - \varepsilon_{m,\mathbf{k}+\mathbf{q}} + \hbar\omega_{\mathbf{q}\nu}) \right]$$
(3)

The rate of energy transfer from electrons to phonons, reads:<sup>4, 28, 31</sup>

$$\frac{\delta E}{\delta t} = \Gamma_{em}\omega_{em} - \Gamma_{abs}\omega_{abs} = \frac{2\pi}{\hbar}\Sigma_{m\nu}\int \frac{d\mathbf{q}}{\Omega_{BZ}}\omega_{\mathbf{q}\nu}|g_{mn\nu}(\mathbf{k},\mathbf{q})|^2(N_{\mathbf{q},\nu}+1-f_{m,\mathbf{k}+\mathbf{q}})\delta(\varepsilon_{n,\mathbf{k}}-\varepsilon_{m,\mathbf{k}+\mathbf{q}}-\hbar\omega_{\mathbf{q}\nu}) - \frac{2\pi}{\hbar}\Sigma_{m\nu}\int \frac{d\mathbf{q}}{\Omega_{BZ}}\omega_{\mathbf{q}\nu}|g_{mn\nu}(\mathbf{k},\mathbf{q})|^2(N_{\mathbf{q},\nu}+f_{m,\mathbf{k}+\mathbf{q}})\delta(\varepsilon_{n,\mathbf{k}}-\varepsilon_{m,\mathbf{k}+\mathbf{q}}+\hbar\omega_{\mathbf{q}\nu})$$
(4)

	Scattering channel	$\Gamma - L, L - \Gamma$	$\Gamma - X, X - \Gamma$	L - L	X - X	X-L, L-X
MC from $36$	$D^{eff},  \mathrm{eV/\AA}$	10	10	10	7	5
	$\omega_{eff},  \mathrm{meV}$	27.8	29.9	29.0	29.9	29.3
DFT-based,	$D^{eff},  \mathrm{eV/\AA}$	4	4	4	4	4
this work	$\omega_{eff},  \mathrm{meV}$	19	19	19	19	19

Table 1. Effective deformation potentials and phonon frequencies for intervalley scattering in GaAs: MC parameters from Ref. 36 and *ab initio* DFT-based parameters determined in this work.



Figure 1. MC simulation of the evolution with time of the average energy of out-of-equilibrium carrier distributions excited initially at 0.5 eV and 0.7 eV above the conduction band minimum.

In this work, we have used the method of calculation of the electron-phonon matrix elements based on the density functional perturbation theory  $(DFPT)^{32,33}$  and interpolation in the Wannier representation<sup>29,34</sup> using the EPiq code.<sup>23,24,34</sup> All technical details for the DFT-based description of GaAs can be found in 24.

The effective electron-phonon parameters which are necessary to couple the DFT-based data with MC approach, can be obtained from the quantities of eqns. 2 and 3, calculated for specific scattering channel, i.e. for specific phonon modes and/or for specific parts of the Brillouin zone:<sup>2</sup>

$$|g_{n,\mathbf{k}}^{eff}| = \sqrt{\Gamma_{n,\mathbf{k}}/FDOS_{n,\mathbf{k}}} \tag{5}$$

The electron-phonon deformation potentials are related to the electron-phonon matrix elements as follows:<sup>35</sup>

$$D^{eff} = \frac{\sqrt{2\rho\Omega\omega_{eff}}}{\hbar} |g^{eff}| \tag{6}$$

Here,  $\rho$  is the mass density of the crystal,  $\Omega$  is the crystal volume,  $\omega_{eff}$  is phonon frequency.

The deformation potentials defined in eq. 6 which are commonly used in MC solvers are empirical parameters adjusted to reproduce the characteristics of the velocity vs. electric field in the stationary regime. The set of parameters defined in Ref. 36 which were used previously in our MC approach and the ones derived from DFT in this work are listed in Table 1.

#### 3. RESULTS

Although the electron-phonon matrix elements calculated with DFT methods depend on both the electronic and phonon states, the averaging procedure of eq. 5 which included all phonon modes and was limited to intervalley processes (i.e. phonons with  $|\mathbf{q}| > 0.25 \frac{2\pi}{a}$ , where *a* is lattice parameter) allowed us to conclude that, for the dominant intervalley channels in GaAs, the dependence of the effective electron-phonon matrix elements on the initial electronic state was weak. Finally, our DFT calculations allowed us to choose the constant value of  $D_{eff}^{dft} = 4 \text{ eV}/\text{\AA}$  as representative of the strength of the electron-phonon intervalley coupling in GaAs. One can notice from table 1 that the average strength of the intervalley scattering and the effective phonon frequencies



Figure 2. MC simulation of the evolution with time of the energy transfer rate from electrons to phonons, for the out-ofequilibrium carrier distributions excited initially at 0.7 eV (upper panel) and 0.5 eV (lower panel) above the conduction band minimum. The energy transfer rate curves were obtained from the average energy curves shown in Fig. 1. The values of the energy transfer rate from photoexcited electrons to phonons in GaAs, measured in Ref. 4 using time-resolved photoemission are indicated by the green lines.

determined with DFT differ strongly from the values used initially in MC simulation of Ref. 36. This difference is expected to have a strong impact on the transient regime at high carrier energy.

The results of the time-dependent MC simulation of the evolution with time of the average energy of out-ofequilibrium carrier distributions excited initially at 0.5 eV and 0.7 eV above the conduction band minimum are plotted in Fig. 1. The initial electronic distributions were modeled by Gaussian functions centered around 0.5 eV and 0.7 eV excess energies. We compare the MC results obtained with the intervalley scattering constants presented in table 1: the ones of Ref. 36 (solid curves) and the ones determined in this work on the basis of DFT description (dashed curves). As one can see in Fig. 1, as expected, the change in the intervalley scattering constant and in effective frequencies reduces strongly the energy transfer rate from electrons to phonons, due to the dominant role of the intervalley scattering in the energy transfer from photoexcited electrons to phonons.<sup>4</sup> Also as expected, the energy transfer rate is found to reduce with time, as the electron distribution approaches equilibrium.

In Fig. 2, we show the evolution with time of the energy transfer rate from electrons to phonons, for the same out-of-equilibrium carrier distributions as in Fig. 1. The energy transfer rate curves were obtained from the average energy curves shown in Fig. 1. As one can see in Fig. 2, at early times, the change in the intervalley scattering constant strength changes strongly the energy transfer rate from electrons to phonons.<sup>4</sup> Interestingly, as one can see in Fig. 2, for time values greater than 0.4 ps, the energy transfer rate is not affected by the drastic change in the intervalley scattering parameters. Finally, as shown in Fig. 2, our MC results using  $D_{eff}^{dft}$  are found in good agreement with the experimental energy transfer rate from photoexcited electrons to phonons, which was measured in Ref. 4 using time-resolved photoemission.

#### 4. CONCLUSION

In conclusion, we have presented the results of a successful coupling of the stochastic MC simulation with DFTbased description of the intervalley electron-phonon coupling in GaAs. We find that the change in the intervalley scattering constant strength changes strongly the energy transfer rate from electrons to phonons for times smaller than 0.4 ps, and that the MC results using DFT values are found in good agreement with the experimental energy transfer rates from photoexcited electrons to phonons, which were measured with time-resolved photoemission. Moreover, we find that, for the rate of energy transfer from electrons to phonons, the steady state is not affected by the change is the intervalley scattering description, in contrast to transient state.

#### ACKNOWLEDGMENTS

The support from ANR via ANR-21-CE50-0008 (PLACHO project) is gratefully acknowledged.

The access to high performance computing resources was granted by the French HPC centers GENCI-IDRIS, GENCI-CINES and GENCI-TGCC (Project 2210) and by the École Polytechnique through the 3 Lab Computing project.

The DFT calculations were performed using the Quantum ESPRESSO,<sup>33</sup> EPIq<sup>23</sup> and Wannier90<sup>37</sup> packages.

#### REFERENCES

- Giustino, F., "Electron-phonon interactions from first principles," Rev. Mod. Phys. 89, 015003 (2017). And references herein.
- [2] Sjakste, J., Tanimura, K., Barbarino, G., Perfetti, L., and Vast, N., "Hot electron relaxation dynamics in semiconductors: assessing the strength of the electron-phonon coupling from the theoretical and experimental viewpoints," J. Phys.: Condens. Matter 30, 353001 (2018).
- [3] Poncé, S., Li, W., Reichardt, S., and Giustino, F., "First-principles calculations of charge carrier mobility and conductivity in bulk semiconductors and two-dimensional materials," *Rep. Prog. Phys.* 83, 036501 (2020).
- [4] Sjakste, J., Vast, N., Barbarino, G., Calandra, M., Mauri, F., Kanasaki, J., Tanimura, H., and Tanimura, K., "Energy relaxation mechanism of hot-electron ensembles in GaAs: Theoretical and experimental study of its temperature dependence," *Phys. Rev. B* 97, 064302 (2018).
- [5] Chen, Z., Sjakste, J., Dong, J., Taleb-Ibrahimi, A., Rueff, J.-P., Shukla, A., Peretti, J., Papalazarou, E., Marino, M., and Perfetti, L., "Ultrafast dynamics of hot carriers in a quasi-two-dimensional electron gas on inse," *PNAS* **117**, 21962–21967 (2020).
- [6] Tanimura, H., Kanasaki, J., Tanimura, K., Sjakste, J., Vast, N., Calandra, M., and Mauri, F., "Formation of hot-electron ensembles quasiequilibrated in momentum space by ultrafast momentum scattering of highly excited hot electrons photoinjected into the  $\Gamma$  valley of GaAs," *Phys. Rev. B* **93**, 161203(R) (2016).
- [7] Caruso, F. and Novko, D., "Ultrafast dynamics of electrons and phonons: from the two-temperature model to the time-dependent Boltzmann equation," ADVANCES IN PHYSICS: X 7, 2095925 (2022).
- [8] Maldonado, P., Carva, K., Flammer, M., and Oppeneer, P. M., "Theory of out-of-equilibrium ultrafast relaxation dynamics in metals," *Phys. Rev. B* 96, 174439 (2017).
- [9] Jhalani, V., Zhou, J., and Bernardi, M., "Ultrafast hot carrier dynamics in GaN and its impact on the efficiency droop," *Nano Lett.* 17, 5012–5019 (2017).
- [10] Wadgaonkar, I., Wais, M., and Battiato, M., "Numerical solver for the out-of-equilibrium time dependent Boltzmann collision operator: Application to 2d materials," *Computer Physics Communications* 271, 108207 (2022).
- [11] Maliyov, I., Park, J., and Bernardi, M., "Ab initio electron dynamics in high electric fields: Accurate prediction of velocity-field curves," *Phys. Rev. B* 104, L100303 (2021).
- [12] Murphy-Armando, F., Murray, E. D., Savić, I., Trigo, M., Reis, D. A., and Fahy, S., "Electronic heat generation in semiconductors: Non-equilibrium excitation and evolution of zone-edge phonons via electron-phonon scattering in photo-excited germanium," *Appl. Phys. Lett.* **122**, 012202 (2023).

- [13] Zürch, M., Chang, H.-T., Borja, L. J., Kraus, P. M., Cushing, S. K., Gandman, A., Kaplan, C. J., Oh, M. H., Prell, J. S., Prendergast, D., Pemmaraju, C. D., Neumark, D. M., and Leone, S. R., "Direct and simultaneous observation of ultrafast electron and hole dynamics in germanium," *Nat. Commun.* 8, 15734 (2017).
- [14] Wörle, M., Holleitner, A. W., Kienberger, R., and Iglev, H., "Ultrafast hot carrier relaxation in silicon monitored by phase-resolved transient absorption spectroscopy," *Phys. Rev. B* 104, L041201 (2021).
- [15] Cavalieri, A. L., Müller, N., Uphues, T., Yakovlev, V. S., Baltuška, A., Horvath, B., Schmidt, B., Blümel, L., Holzwarth, R., Hendel, S., Drescher, M., Kleineberg, U., Echenique, P. M., Kienberger, R., Krausz, F., and Heinzmann, U., "Attosecond spectroscopy in condensed matter," *Nature* 449, 1029 (2007).
- [16] Ossiander, M., Riemensberger, J., Neppl, S., Mittermair, M., Schäffer, M., Duensing, A., Wagner, M. S., Heider, R., Wurzer, M., Gerl, M., Schnitzenbaumer, M., Barth, J. V., Libisch, F., Lemell, C., ürfer, J. B., Feulner, P., and Kienberger, R., "Absolute timing of the photoelectric effect," *Nature* 561, 374 (2018).
- [17] Nozik, A. J., "Utilizing hot electrons," Nature Energy 3, 170 (2018).
- [18] Tsai, C. Y., "Carrier heating and its effects on the current-voltage relations of conventional and hot-carrier solar cells: A physical model incorporating energy transfer between carriers, photons, and phonons," *Solar Energy* 188, 450 (2019).
- [19] Fischetti, M. V. and Laux, S. E., "Monte Carlo analysis of electron transport in small semiconductor devices including band-structure and space-charge effects," *Phys. Rev. B* 38, 9721 (1988).
- [20] Dollfus, P., Bru, C., and Hesto, P., "Monte Carlo simulation of pseudomorphic InGaAs/GaAs high electron mobility transistors: Physical limitations at ultrashort gate length," J. App. Phys. 73, 804 (1993).
- [21] Aubry-Fortuna, V. and Dollfus, P., "Electron transport properties in high-purity ge down to cryogenic temperatures," J. Appl. Phys. 108, 123706 (2010).
- [22] Pilotto, A., Antonelli, M., Arfelli, F., Biasiol, G., Cautero, G., Cautero, M., Colja, M., Driussi, F., Esseni, D., Menk, R. H., Nichetti, C., Rosset, F., Selmi, L., Steinhartova, T., and Palestri, P., "Modeling approaches for gain, noiseand time response of avalanchephotodiodes for x-rays detection," *Frontiers in Physics* 10, 944206 (2022).
- [23] Marini, G., Marchese, G., Profeta, G., Sjakste, J., Macheda, F., Vast, N., Mauri, F., and Calandra, M., "Epiq: An open-source software for the calculation of electron-phonon interaction related properties," *Comp. Phys. Comm.* 295, 108950 (2024).
- [24] Sjakste, J., Vast, N., Calandra, M., and Mauri, F., "Wannier interpolation of the electron-phonon matrix elements in polar semiconductors: Polar-optical coupling in GaAs," *Phys. Rev. B* 92, 054307 (2015).
- [25] Sen, R., Vast, N., and Sjakste, J., "Hot electron relaxation and energy loss rate in silicon: Temperature dependence and main scattering channels," *Appl. Phys. Lett.* **120**, 082101 (2022).
- [26] Cheng, P. S., Sun, J., Sun, S.-N., Choi, A. Y., and Minnich, A. J., "High-field transport and hot-electron noise in gaas from first-principles calculations: Role of two-phonon scattering," *Phys. Rev. B* 106, 245201 (2022).
- [27] Sun, J. and Minnich, A. J., "Transport and noise of hot electrons in gaas using a semianalytical model of two-phonon polar optical phonon scattering," *Phys. Rev. B* 107, 205201 (2023).
- [28] Allen, P., "Theory of thermal relaxation of electrons in metals," *Phys. Rev. Lett.* 59, 1460 (1987).
- [29] Ponce, S., Margine, E. R., Verdi, C., and Giustino, F., "EPW: Electron-phonon coupling, transport and superconducting properties using maximally localized Wannier functions.," *Comp. Phys. Comm.* 209, 116 (2016).
- [30] Poncé, S., Macheda, F., Margine, E., Marzari, N., Bonini, N., and Giustino, F., "First-principles predictions of Hall and drift mobilities in semiconductors," *Phys. Rev. Research* 3, 043022 (2021).
- [31] Ahmad, S., Daga, O., and Khokle, W., "Energy and momentum loss rates for hot electrons in silicon.," *Phys. Stat. Sol.* 40, 631 (1970).
- [32] Baroni, S., de Gironcoli, S., Corso, A. D., and Giannozzi, P., "Phonons and related crystal properties from density-functional perturbation theory," *Rev. Mod. Phys.* 73, 515 (2001).

- [33] Giannozzi, P., Andreussi, O., Brumme, T., Bunau, O., Nardelli, M. B., Calandra, M., Car, R., Cavazzoni, C., Ceresoli, D., Cococcioni, M., Colonna, N., Carnimeo, I., Corso, A. D., de Gironcoli, S., Delugas, P., Ferretti, R. A. D. J. A., Floris, A., Fratesi, G., Fugallo, G., Gebauer, R., Gerstmann, U., Giustino, F., Gorni, T., Jia, J., Kawamura, M., Ko, H.-Y., Kokalj, A., Küçükbenli, E., Lazzeri, M., Marsili, M., Marzari, N., Mauri, F., Nguyen, N. L., Nguyen, H.-V., de-la Roza, A. O., Paulatto, L., Poncé, S., Rocca, D., Sabatini, R., Santra, B., Schlipf, M., Seitsonen, A. P., Smogunov, A., Timrov, I., Thonhauser, T., Umari, P., Vast, N., Wu, X., and Baroni, S., "Advanced capabilities for materials modelling with QUANTUM ESPRESSO," J. Phys.: Condens. Matter 29, 465901 (2017).
- [34] Calandra, M., Profeta, G., and Mauri, F., "Adiabatic and nonadiabatic phonon dispersion in a Wannier approach," Phys. Rev. B 82, 165111 (2010).
- [35] Zollner, S., Gopalan, S., and Cardona, M., "Microscopic theory of intervalley scattering in GaAs: kdependence of deformation potentials and scattering rates," J. Appl. Phys. 68, 1682 (1990).
- [36] Littlejohn, M. A., Hauser, J. R., and Glisson, T. H., "Velocity-field characteristics of gaas with  $\gamma_6^c l_6^c x_6^c$  conduction-band ordering," *J. Appl. Phys.* **48**, 4587 (1977).
- [37] Pizzi, G., Vitale, V., Arita, R., Blugel, S., Freimuth, F., Géranton, G., Gibertini, M., Gresch, D., Johnson, C., Koretsune, T., Ibañez-Azpiroz, J., Lee, H., Lihm, J. M., Marchand, D., Marrazzo, A., Mokrousov, Y., Mustafa, J. I., Nohara, Y., Nomura, Y., Paulatto, L., Poncé, S., Ponweiser, T., Qiao, J., Thole, F., Tsirkin, S. S., Wierzbowska, M., Marzari, N., Vanderbilt, D., Souza, I., Mostofi, A. A., and Yates, J. R., "Wannier90 as a community code: new features and applications," *J. Phys.: Condens. Matter* **32**, 165902 (2020).